

REPRODUCIBLE METHODS TO EXCEED THE PERFORMANCE OF SINGLE-JUNCTION SOLAR CELLS

**Mr.S.FAROOK
BASHA,**
ASSISTANT
PROFESSOR
SVR Engineering
College,Nandyal.

**Mrs M. ARUNA
JYOTHI,**
ASSISTANT
PROFESSOR
SVR Engineering
College,Nandyal.

Mr.S.ABDUL JABBER
ASSISTANT
PROFESSOR
SVR Engineering
College,Nandyal.

Abstract

In a future with zero emissions of carbon dioxide, solar photovoltaics will be the primary method used to generate electricity.1 Silicon sun cells now have a dominant position in the market for large-scale solar power production. At the same time, high-performance lab-scale devices are approaching the limit of their detailed-balance efficiency.2 Because of falling module costs, three-cell efficiency is becoming more essential as a driver for further reductions in the levelized cost of energy. This gives rise to an increase in the value of three-cell efficiency.

Therefore, the goal of the next generation of solar cells is to achieve an efficiency that is greater than that of single-junction solar cells. Despite the fact that multi-junction solar cells, such as those based on III-V materials, are currently exceedingly efficient, the cost of these materials has prevented their widespread use due to their exorbitant expense.4 In this particular subtopic, we instead concentrate on emerging technologies and materials that provide the prospect of surpassing the efficiency limit of a single junction in a scaled (multi-km²) manner in the future. This is because we believe that this is the most important factor.

Introduction

The detailed-balance single-junction efficiency limit is based on the assumption that a solar cell consists of a single absorber layer. In this kind of solar cell, each incoming photon yields a single electron-hole pair that may be extracted and used to accomplish work.5 Every popular strategy that goes beyond this limit violates at least one of these

assumptions in one of two ways: either it uses two or more absorber layers with distinct optical bandgaps or it enables the creation of more than a single electron-hole pair. Both of these things are done in order to make the most efficient use of the vast solar spectrum. The resultant solar cells that are discussed in this special subject collection may be classified into two primary groups, namely tandem solar cells and solar cells that use up- or downconversion (Fig. 1). Tandem solar cells are characterised by the presence of two solar cells that are connected in series to provide a single output voltage. In this article, we compile information on scalable strategies to overcome restrictions posed by single-junction solar cells utilising the aforementioned methodologies.

A tandem solar cell is made up of two separate subcells, each of which has its own bandgap and its own junction to assist in the separation of electrons and holes.6 There are a few distinct pathways to link the two sub-cells together. For example, they may be electrically separate and merely optically connected (four-terminal cell, or 4T), which enables the independent power created by each cell to be combined outside. This configuration is known as a "four-terminal cell." Alternately, they may

be electrically linked in series (also known as a two-terminal cell, or 2T), in which case the voltages will inherently add up to the total but the currents will need to be matched. Other geometries, such as cells with three terminals, are seen far less often. Tandem cells have the potential to play a significant role in the rapid deployment of photovoltaic (PV) systems in the not too distant future.

The purpose of solar photovoltaic (PV) technologies is to generate power without releasing a significant amount of greenhouse gases; nevertheless, in order to meet the objectives of the Paris Agreement⁷, there has to be a rapid shift towards the production of electricity using lower amounts of carbon.⁸ Because of this, new technologies that are compatible with already-existing technologies, industrial facilities, and markets have an edge when it comes to implementation. Perovskite/silicon tandem solar cells are shown to fulfil several of these conditions, as shown by Kamaraki and colleagues.⁹ The writers are all employed at Oxford PV, the business that is responsible for commercialising the technology. They argue that the most economically feasible configuration for a tandem cell is a 2T configuration, and the reason for this is because a 4T configuration would need twice as many inverters, which would be prohibitively expensive in the current market. Si solar cells are selected as the most promising bottom cell due to the fact that they now dominate the market, have a track record of providing reliable performance over a long period of time, and are very inexpensive. For the top cell, it is not sufficient for the cell to be efficient or low-cost; rather, the cell must be both, especially in terms of its level of comparability to the bottom cell's

efficiency. They explain how a metal halide behaves as a result.




FIG. 1. Working principle of a tandem solar cell (left) and an up- and downconversion-based solar cell (right). The tandem cell consists of two separate sub-cells, often the bottom cell is made of silicon and absorbs the low-energy part of the solar spectrum, and the top cell absorbs the higher-energy photons. The up- and down conversion cell often only consists of one solar cell junction, while the up- and downconversion layers transform the incident spectrum so that it can be better converted by the cell.

perovskite top cell potentially fulfills these requirements since high-quality films can be formed by a variety of simple, low-cost deposition techniques. In addition, the technological compatibility of perovskite cells with the existing and highly developed Si industry allows these tandems to leverage the decades of development in Si cells and module fabrication, as well as systems and business development. An important commercial consideration is that perovskite/Si tandem modules offer a higher efficiency than traditional Si-only modules, which allows the producer to charge a premium in applications where space is limited such as in rooftop systems. After market introduction, they emphasize that the learning curve of the tandem cells needs to keep pace with Si-only cells to remain competitive. They are

optimistic that large efficiency potential and the connection to the established, large-scale Si industry should make this possible.

There are still several materials challenges to overcome before perovskite-based tandem cells become a reality. Several of these are addressed in this special topic collection. A high photoluminescence quantum yield (PLQY) is critical for all solar cell materials. Perovskites often show high PLQY, but it can be diminished by sample morphology and material purity. Screening material compositions and fabrication techniques, therefore, requires a rapid method to study the PLQY of a perovskite sample. Akhundova et al. show that the spectral shape of the photoluminescence (PL) from wide-bandgap perovskites correlates with the PLQY of a sample.¹⁰ The authors assign this correlation to the observation both the PLQY and the spectral shape reflect the domain size dispersion because of its role in the funneling of carriers into trap sites. The size dispersion is greatly affected by processing parameters such as annealing conditions, and these results highlight the importance of carefully controlling fabrication.

The fabrication of perovskite thin films needs to be scalable without compromising luminescence efficiency. Ishteev et al. demonstrate a new deposition technique for all-inorganic, large-bandgap perovskite thin films.¹¹ They fabricate the precursors, CsBr and PbBr₂, by dry, mechanical milling before deposition in a single-source CVD process under mild vacuum (0.02–1.00 mBar). All these techniques are, in principle, scalable, and the authors are able to vary the ratio between the precursors (i.e., CsBr:PbBr₂) to search for the most luminescent

composition. They observe greatest brightness from a 35:65 ratio, a composition that forms both the CsPb₂Br₅ and CsPbBr₃ perovskites. They demonstrate that this technique can be used to conformally coat textured surfaces but identify that the stability and PLQY will require further improvements.

For the full device stack, perovskite tandem cells require transparent electrodes (4T) and interconnection layers (2T). These layers have received considerable attention because of their importance for the overall performance. The interconnection layer between the two sub-cells of a 2T tandem cell ideally offers good recombination properties, while transmitting all low-energy light. Koc, et al. calculate the optical transmission of an interconnection layer consisting of thin Ag between two transport layers in a perovskite-perovskite tandem cell.¹² They report transfer matrix calculations that explore the transmission of light into the low-bandgap bottom cell when the thicknesses of the silver layer and the adjacent transport layers are varied. They find two tradeoffs. First, the refractive index of the transfer layers is important to the transmission of light. Ideally, the index would be larger than 1.9; however, by the Kramers–Kronig relationship, these high indices will also lead to larger parasitic absorption. Second, the silver layer should be as thin as possible for good light transmission (even 3 nm already reduces the photocurrent from the bottom cell), but thicker layers lead to larger lateral conductivity.

For 4T tandem cells, the top cell needs to be fully transparent to below-bandgap light. However, the transparent conductive electrode required induces large parasitic absorption and often used indium-tin oxide

(ITO) is too brittle to be implemented in flexible solar cells. As in the previous example for interconnection layers, thin metal layers can also perform as excellent transparent conductive electrodes. Spinelli et al. sandwich a sputtered layer of Ag or co-sputtered Ag/Cu between two layers of ITO, and these ITO-Cu/Ag-ITO electrodes show a NIR transmission similar to ITO when the layer thicknesses are optimized.¹³ They perform this using transfer-matrix modeling, identifying an optimal transmission for thicknesses of 40 nm for the first ITO layer, 5 nm for the metal, and 65 nm for the second ITO layer. The layers were then processed in a full device stack with a large-bandgap perovskite as the active layer and performed slightly better than the same device with an ITO contact. In addition, they find that the initial sheet resistance of the ITO-metal-ITO contact is about half that of pure ITO (200 nm), and it retains this value upon repeated bending cycles, while the ITO resistance doubles after about 1000 cycles. The authors work for Saule Technologies, a company commercializing perovskite solar cell products, and they are confident that this contact architecture can provide a scalable and efficient solution for applications.

While perovskite/silicon and perovskite/perovskite tandem cells receive significant attention from the research community because of their potential for implementation at scale in large-area photovoltaics, different tandem configurations offer interesting properties for other applications. For example, III-V semiconductor/Si tandem solar cells combine a low-cost and well-established Si bottom cell with a highly efficient III-V top cell. While too expensive for large-area applications, these cells might suit the

high-performance end of the market, for example, for vehicle-integrated PV. Whitehead et al. fabricate a 4T GaAs/Si tandem cell that is mechanically stacked by combining various thicknesses of GaAs with a Si cell that features interdigitated back contacts.¹⁴ The 4T configuration is necessary here, because the bandgap of GaAs is too low for a current-matched 2T combination with Si. The back-contacted silicon cell makes the stacking and contacting easier. The authors find that the tandem cell efficiency does not depend too heavily on the GaAs thickness as long as it is thicker than 1.9 μm . All tandem cells show excellent performance with $>30\%$ power conversion efficiency, and their cell with 2.8 μm GaAs shows the highest tandem efficiency (32.57%). The performance for the various layer thicknesses is confirmed with transfer matrix modeling for the optical transmission and absorption, Lambertian light-trapping for the Si cell, and the Hovel method to study the effect of photon recycling. The low refractive index of the glass interlayer ensures that the GaAs cell benefits from the effect of photon recycling by trapping the emitted light inside the top cell.

Like tandem solar cells, two or more effective bandgaps are also required for the up- and downconversion schemes. However, only one of them needs to form a semiconductor junction to extract charge. The other bandgap can then be used to down-convert the energy if the bandgap is higher than the one that forms the junction or upconvert if it is lower. There are several mechanisms for both up- and downconversion. In this special topic collection, we find contributions on singlet fission and multiple exciton generation

as downconversion processes, and triplet-triplet annihilation and intermediate-gap solar cells as upconversion processes.

Singlet fission is a process that can be used in photon downconversion, and the most thoroughly studied materials are crystalline, conjugated small molecules such as the linear acenes. Photon absorption in these materials initially generates spin-singlet excitons. These are converted by fission into pairs of lower-energy spin-correlated triplet excitons.¹⁵ The process is spin-allowed and is, hence, can be rapid and efficient in materials where it is energetically favorable.¹⁶ In that respect, singlet fission appears to be an ideal downconversion mechanism when combined with a low-bandgap solar cell. In practice, however, multiple challenges arise when implementing these organic materials in a practical solar cell architecture. Cheung and Kaake investigate the effect of the exciton binding energy and endothermicity on the potential solar cell efficiency.¹⁷ The binding energy comes from the Coulombic interaction between the electron and hole of the exciton. The endothermicity, also called entropic gain, is observed in many singlet fission materials and stems from the greater number of microstates possible when one singlet exciton converts into two triplet excitons.¹⁸ The authors use both the optical gaps of the singlet fission material and the low-bandgap solar cell as free parameters in a detailed-balance based efficiency calculation and assume charge transfer from the triplet exciton to generate current. They find that in simple two-bandgap systems, the efficiency drop from the exciton binding energy can be partially recovered by the endothermicity. However, at high exciton binding energies (e.g., 0.5 eV), the maximum achievable

efficiency drops from 43.9% to 31.0% even assuming an effective endothermicity of 0.25 eV. Then, a double heterojunction is introduced with a bridge molecule that serves to accept electrons from the triplet excitons, much like in ternary blend organic solar cells.¹⁹ This bridge molecule reduces recombination and aids charge separation. The result is that the maximum achievable solar cell performance remains high even at high exciton binding energies. Revisiting the example mentioned previously, with 0.5 eV exciton binding energy and 0.25 eV endothermicity, they show that the bridge molecules would lift the efficiency potential from 31.0% to well above 40%. While charge separation from singlet fission-generated triplet excitons may lead to high efficiency,²⁰ the most promising experimental realizations with singlet fission and silicon cells so far rely on energy transfer.²¹

Many downconversion processes are technically multiple-exciton generation processes, but conventionally the term multiple exciton generation (MEG) refers to the inverse Auger process in inorganic semiconductors that generates two or more band edge electron-hole pairs from one high-energy photoexcitation. This process is inefficient in bulk materials both energetically and in terms of quantum yield, but prospects are improved in colloidal quantum dots due to factors that include improved momentum matching.²² Solar cells utilizing MEG to achieve greater-than-unity photon-to-carrier yield at select wavelengths have been demonstrated²³ but have not yet reached high energy-conversion efficiencies. Writing in this collection, Pusch et al. show that equilibrium-only models are insufficient in assessing the efficiency potential of such cells, because of the

voltage dependence of the inverse process of MEG, Auger recombination.²⁴ As voltage increases, Auger recombination starts to play a larger role. In contrast, all relevant processes in conventional solar cells are well separated in time. In these conventional cases, the external quantum efficiency measured at short circuit can be used to calculate the photocurrent, and the superposition principle applies. However, when the efficiency potential of MEG solar cells is assessed, microscopic reversibility must be explicitly considered to properly treat the interplay between MEG and Auger recombination. Pusch et al. devise a model that incorporates these considerations for a quantum dot-based device assuming equidistant, discrete energy levels. This model reproduces experimentally observed EQE curves, and they show that the quasi-Fermi level splitting varies across the device due to the microscopic reversibility. The MEG process, thus, depends on the applied voltage, and as a result, the calculated IV curves show a lower open-circuit voltage compared to a model that assumes equilibrium conditions. Inclusion of trion states to the Auger recombination rate further reduces the efficiency potential, so preventing these charged states in devices will be critical to achieve significant efficiency gains over single-junction solar cells.

MEG and singlet fission both harness high-energy photons to generate multiple excitons of lower energy. In principle, direct extraction of the energy of hot carriers is also possible. There are major challenges, however, which are in part related to the generally rapid relaxation of hot carriers to the band edge. Esmailpour et al. investigate the hot-carrier relaxation in type-II InAs/AlAsSb multi-quantum

well structures.²⁵ They study the effect of different barrier thicknesses on hot carrier relaxation by measuring the PL spectrum at different excitation intensities. By measuring the excess temperature from the PL spectrum for different barrier layer thicknesses, they find that the barrier layer thickness has an effect of the effective temperature because of changes in the cooling rates. The authors explain this difference by a difference in phonon scattering rates. Supported by DFT calculations, they find that the larger barrier layers (higher InAs/AlSb ratio) show a reduced phonon density of states, which leads to an increase in the phonon scattering time.

While all the previous examples aim to make better use of the high-energy part of the solar spectrum, upconversion does the opposite. In such schemes, below-bandgap photons are absorbed in an upconverter material and transformed into higher-energy photons or excitations. An attractive strategy for incoherent photon upconversion efficiencies is based on triplet-triplet annihilation (TTA), also known as triplet fusion, where pairs of spin-triplet excitons are combined to form a higher-energy, emissive spin-singlet exciton. The most efficient schemes have relied on external sensitizers that absorb incident light and then transfer this energy to annihilator/emitter molecules. Traditionally, these schemes relied on metal-organic complexes to serve as sensitizers,²⁶ and more recently colloidal quantum dots^{27,28} and lanthanide-doped nanoparticles sensitizers combined with organic emitters.²⁹ With the rise of perovskites as the dominant thin-film semiconductor (at least in the research community), perovskite nanocrystals³⁰ and films³¹ have also now been used as

sensitizers for TTA upconversion. Surprisingly, even bulk perovskites performed very efficiently thanks to their high charge carrier mobility and long charge carrier lifetimes. For applications in solar cells, these upconversion systems need to work efficiently at sub-solar fluxes and under continuous illumination. Writing in this collection, Vanorman et al. study the effect of illumination on the efficiency of a (MAFA)PbI₃ perovskite/rubrene upconversion bilayer.³² They show that the continued illumination improves the upconversion efficiency, which correlates with an increase in the total perovskite PL that is associated with the relative suppression of short-lifetime decay channels. This is consistent with trap filling within the perovskite layer, because populating the triplet excitons in rubrene by the perovskite excitations competes with trapping within the perovskite and at the interface. Under continued illumination, they observe that the upconversion PL from rubrene rises more rapidly following additional pulsed excitation, providing further evidence that the transfer of energy into the rubrene triplet state is improved. The work highlights that the upconversion efficiency reported in these systems strongly depends on not only the incident power but also the illumination history of the sample.

A theoretically elegant but technically challenging way to overcome the efficiency limit of single-junction solar cells is the concept of intermediate-gap solar cells.^{33,34} Here, a state within the bandgap of the absorber layer is used to provide a second absorption gap. The intrinsic challenge in this architecture is that the reciprocity of absorption and emission processes mean that charges in the intermediate gap typically recombine

faster than photons can be absorbed at solar flux to generate excitations across the bandgap. This issue can be overcome by “parking” electrons in a second level slightly lower than the intermediate gap to prolong their lifetime. Huang et al. investigate theoretically such a system where a bilayer of Sn-doped AgAlTe₂ and LiInTe₂ is also used to aid charge separation in a type-II heterojunction.³⁵ They calculate the band structure of both pure materials and those doped with various group-IV metals. The combination of the Sn-doped materials provides good lattice matching and maintains the type-II heterojunctions of the undoped materials.

Overall, this special topic collection shows the breadth of studies, the novelty, and the creativity that the research community is applying to circumvent the single-junction efficiency limit for solar cells. While some concepts, such as perovskite/silicon tandems, are close to market entry, others, while demonstrated, are not yet commercially viable for large-scale terrestrial applications, such as the III–V based technologies. The up- and downconversion technologies, on the other hand, have enormous potential both for high efficiency and for low cost but are further away from commercial implementation. We embrace this wide range of technologies at different stages of research, and we see a bright future for high-efficiency, large-scale solar cell applications.

We would like to thank all the authors that have contributed and the editors of APL Maria Antonietta Loi and Lesley Cohen as well as Emma Nicholson van Burns and Jessica Trudeau for their assistance.

The work of B.E. was part of the Dutch Research Council (NWO) and was

performed at the research institute AMOLF. The work of J.V.M. is part of the Swiss National Science Foundation (SNSF) PRIMA project performed at the Adolphe Merkle Institute. A.H.-B. would like to acknowledge the support of the Australian Government through the Australian Research Council Future Fellowship (No. FT210100210) and through Australian Renewable Energy Agency (ARENA)-2020/ RND001 and 2020/RND003 projects.

DATA AVAILABILITY

Sharing of data is not relevant to this study since no new data were generated or analysed over the course of this research.

REFERENCES

1. Energy Watch Group, *Global Energy System Based on 100% Renewable Energy* (Energy Watch Group, 2019).
2. B. Ehrler, E. Alarcón-Lladó, S. W. Tabernig, T. Veeken, E. C. Garnett, and A. Polman, *ACS Energy Lett.* 5, 3029 (2020).
3. M. A. Green, *Joule* 3, 631 (2019).
4. A. Polman, M. Knight, E. C. Garnett, B. Ehrler, and W. C. Sinke, *Science* 352, 307 (2016).
5. W. Shockley and H. J. Queisser, *J. Appl. Phys.* 32, 510 (1961).
6. S. M. Bedair, M. F. Lamorte, and J. R. Hauser, *Appl. Phys. Lett.* 34, 38 (1979).
7. J. Rogelj, D. Shindell, K. Jiang, S. Fijita, et al., "Mitigation pathways compatible with 1.5 °C in the context of sustainable development" (published online 2018).
8. P. Friedlingstein, M. O'Sullivan, M. W. Jones, R. M. Andrew, J. Hauck, A. Olsen, G. P. Peters, W. Peters, J. Pongratz, S. Sitch, C. L. Quéré, J. G. Canadell, P. Ciais, R. B. Jackson, S. Alin, L. E. O. C. Aragão, A. Arneeth, V. Arora, N. R. Bates, M. Becker, A. Benoit-Cattin, H. C. Bittig, L. Bopp, S. Bultan, N. Chandra, F. Chevallier, L. P. Chini, W. Evans, L. Florentie, P. M. Forster, T. Gasser, M. Gehlen, D. Gilfillan, T. Gkritzalis, L. Gregor, N. Gruber, I. Harris, K. Hartung, V. Havard, R. A. Houghton, T. Ilyina, A. K. Jain, E. Joetjzer, K. Kadono, E. Kato, V.

- Kitidis, J. I. Korsbakken, P. Landschützer, N. Lefeuvre, A. Lenton, S. Lienert, Z. Liu, D. Lombardozzi, G. Marland, N. Metzl, D. R. Munro, J. E. M. S. Nabel, S. I. Nakaoka, Y. Niwa, K. O'Brien, T. Ono, P. I. Palmer, D. Pierrot, B. Poulter, L. Resplandy, E. Robertson, C. Rödenbeck, J. Schwinger, R. Séférian, I. Skjelvan, A. J. P. Smith, A. J. Sutton, T. Tanhua, P. P. Tans, H. Tian, B. Tilbrook, G. Van Der Werf, N. Vuichard, A. P. Walker, R. Wanninkhof, A. J. Watson, D. Willis, A. J. Wiltshire, W. Yuan, X. Yue, and S. Zaehle, *Earth Syst. Sci. Data* 12, 3269 (2020).
9. C. Kamaraki, M. T. Klug, T. Green, L. Miranda Perez, and C. Case, *Appl. Phys. Lett.* 119, 070501 (2021).
10. F. Akhundova, L. Lučer, A. Osvet, J. Hauch, I. M. Peters, K. Forberich, N. Li, and C. Brabec, *Appl. Phys. Lett.* 118, 243903 (2021).
11. A. Ishteev, L. Luchnikov, D. S. Muratov, M. Voronova, A. Forde, T. Inerbaev, V. Vanyushin, D. Saranin, K. Yusupov, D. Kuznetsov, and A. Di Carlo, *Appl. Phys. Lett.* 119, 071901 (2021).
12. M. Koc, M. Ameri, and S. Yerci, *Appl. Phys. Lett.* 119, 021102 (2021).
13. P. Spinelli, R. Fuentes Pineda, M. Scigaj, T. Ahmad, and K. Wojciechowski, *Appl. Phys. Lett.* 118, 241110 (2021).
14. R. C. Whitehead, K. T. VanSant, E. L. Warren, J. Buencuerpo, M. Rienacker, R. Peibst, J. F. Geisz, and A. C. Tamboli, *Appl. Phys. Lett.* 118, 183902 (2021).
15. M. B. Smith and J. Michl, *Chem. Rev.* 110, 6891 (2010).
16. M. W. B. Wilson, A. Rao, B. Ehrler, and R. H. Friend, *Acc. Chem. Res.* 46, 1330 (2013).
17. J. C. F. Cheung and L. G. Kaake, *Appl. Phys. Lett.* 119, 013301 (2021).
18. N. V. Korovina, C. H. Chang, and J. C. Johnson, *Nat. Chem.* 12, 391 (2020).
19. W. Xu and F. Gao, *Mater. Horiz.* 5, 206 (2018).
20. B. Daiber, K. Van Den Hoven, M. H. Futscher, and B. Ehrler, *ACS Energy Lett.* 6, 2800 (2021).
21. M. Einzinger, T. Wu, J. F. Kompalla, H. L. Smith, C. F. Perkinson, L. Nienhaus, S. Wieghold, D. N. Congreve, A. Kahn, M. G. Bawendi, and M. A. Baldo, *Nature* 571, 90–94 (2019).
22. J. Gao, A. F. Fidler, and V. I. Klimov, *Nat. Commun.* 6, 8185 (2015).

- 23.O. E. Semonin, J. M. Luther, S. Choi, H.-Y. Chen, J. Gao, A. J. Nozik, and M. C. Beard, *Science* 334, 1530 (2011).
- 24.A. Pusch, S. P. Bremner, M. J. Y. Tayebjee, and N. J. E. Daukes, *Appl. Phys. Lett.* 118, 151103 (2021).
- 25.H. Esmailpour, B. K. Durant, K. R. Dorman, V. R. Whiteside, J. Garg, T. D. Mishima, M. B. Santos, I. R. Sellers, J. F. Guillemoles, and D. Suchet, *Appl. Phys. Lett.* 118, 213902 (2021).
- 26.T. N. Singh-Rachford and F. N. Castellano, *Coord. Chem. Rev.* 254, 2560 (2010).
- 27.Z. Huang, X. Li, M. Mahboub, K. M. Hanson, V. M. Nichols, H. Le, M. L. Tang, and C. J. Bardeen, *Nano Lett.* 15, 5552 (2015).
- 28.M. Wu, D. N. Congreve, M. W. B. Wilson, J. Jean, N. Geva, M. Welborn, T. Van Voorhis, V. Bulovi, M. G. Bawendi, and M. A. Baldo, *Nat. Photonics* 10, 31 (2016).
- 29.S. Han, R. Deng, Q. Gu, L. Ni, U. Huynh, J. Zhang, Z. Yi, B. Zhao, H. Tamura, A. Pershin, H. Xu, Z. Huang, S. Ahmad, M. Abdi-Jalebi, A. Sadhanala, M. L. Tang, A. Bakulin, D. Beljonne, X. Liu, and A. Rao, *Nature* 587, 594 (2020).
- 30.X. Luo, Y. Han, Z. Chen, Y. Li, G. Liang, X. Liu, T. Ding, C. Nie, M. Wang, F. N. Castellano, and K. Wu, *Nat. Commun.* 11, 28 (2020).
- 31.L. Nienhaus, J. P. Correa-Baena, S. Wieghold, M. Einzinger, T. A. Lin, K. E. Shulenberger, N. D. Klein, M. Wu, V. Bulovic, T. Buonassisi, M. A. Baldo, and M. G. Bawendi, *ACS Energy Lett.* 4, 888 (2019).
- 32.Z. A. Vanorman, J. Lackner, S. Wieghold, K. Nienhaus, G. U. Nienhaus, and L. Nienhaus, *Appl. Phys. Lett.* 118, 203903 (2021).
- 33.A. Luque and A. Mart'i, *Phys. Rev. Lett.* 78, 5014 (1997).
- 34.Y. Okada, N. J. Ekins-Daukes, T. Kita, R. Tamaki, M. Yoshida, A. Pusch, O. Hess, C. C. Phillips, D. J. Farrell, K. Yoshida, N. Ahsan, Y. Shoji, T. Sogabe, and J. F. Guillemoles, *Appl. Phys. Rev.* 2, 021302 (2015).
- 35.D. Huang, L. Ding, Y. Xue, J. Guo, Y. J. Zhao, and C. Persson, *Appl. Phys. Lett.* 118, 043901 (2021).